

Low-cost FeNi₃@C for DSSC counter electrodes

C.-C. Chen
Department of
Environmental
Engineering,
National Cheng Kung
University
Tainan, Taiwan
a91030310@yahoo.com.tw

Y.-F. Liou
Department of
Environmental
Engineering,
National Cheng Kung
University
Tainan, Taiwan
star.ryf127@gmail.com

L.-W. Wei
Department of
Environmental
Engineering,
National Cheng Kung
University
Tainan, Taiwan
wei3532607@gmail.com

H. Paul Wang
Department of
Environmental
Engineering,
National Cheng Kung
University
Tainan, Taiwan
wanghp@ncku.edu.tw

Abstract

To reduce the cost of a dye-sensitized solar cell (DSSC), noble metal platinum (Pt) on the counter-electrode has been replaced with relatively cheap metals, i.e., photo-activity-designable bimetal core-shell nanoparticles. In present work, nickel and iron encapsulated within carbon-shell (FeNi₃@C) nanoparticles were prepared by carbonization of Ni²⁺ and Fe³⁺-β-cyclodextrin at 673 K for the DSSC counter-electrode. By component fitted X-ray absorption near-edge structure (XANES) spectroscopy, metallic nickel (Ni) and iron (Fe (73%) and Fe₃O₄ (27%)) are observed in the FeNi₃@C. The FeNi₃@C nanoparticles are deposited on a conductivity glass recovered from thin film transistor (TFT) liquid crystal display wastes for the counter-electrode of a DSSC. The DSSC having the FeNi₃@C nanoparticles coated counter-electrode has the conversion efficiencies of 3.1%. In addition, the cost of the DSSC using the recycled conducting glass and cheaper nanostructured FeNi₃@C electrode can be reduced by at least 38%.

Keywords: Dye-sensitized solar cells, FeNi₃@C, DSSC counter-electrode.